



## DESCRIPTION

Xypex is a unique chemical treatment for the waterproofing, protection and repair of concrete. XYPEX MODIFIED can be applied as a second coat to reinforce Xypex Concentrate, or applied by itself to damp-proof the exterior of foundation walls. Applied as a second coat, Xypex Modified chemically reinforces Xypex Concentrate where two coats are required and produces a harder finish. Where damp-proofing is required, a single coat of Modified may be used as an alternative to a spray/tar emulsion. Xypex prevents the penetration of water and other liquids from any direction by causing a catalytic reaction that produces a non-soluble crystalline formation within the pores and capillary tracts of concrete and cement-based materials.

## RECOMMENDED FOR:

Xypex Modified is recommended as a single coat for the damp-proofing of foundations or as a second coat with Xypex Concentrate for the following applications:

- Reservoirs
- Sewage and Water Treatment Plants
- Secondary Containment Structures
- Tunnels and Subway Systems
- Underground Vaults
- Foundations
- Parking Structures
- Swimming Pools
- Roof Decks

## ADVANTAGES

- Resists extreme hydrostatic pressure
- Becomes an integral part of the substrate
- Allows concrete to breathe
- Resistant to aggressive chemicals
- Non-toxic
- Does not require dry weather or a dry surface
- Cannot puncture, tear or come apart at the seams
- No costly surface priming or levelling prior to application
- Does not require sealing, lapping and finishing of seams at corners, edges or between membranes
- Can be applied to the positive or the negative side Of the concrete surface
- ♣ Does not require protection during backfilling or during placement of steel, wire mesh or other materials
- ♣ Less costly to apply than most other methods
- ♣ Not subject to deterioration
- ♣ Permanent

## PACKAGING

Xypex Modified is available in 20 kg buckets.

## STORAGE

Xypex products must be stored dry at a minimum temperature of 7°C. Shelf life is one year when stored under proper conditions.

## COVERAGE

For normal surface conditions, the coverage rate for each coat is 0.65 – 0.8 kg/m<sup>2</sup>

## TEST DATA

When used in conjunction with Xypex Concentrate:

## PERMEABILITY

*U.S. Army Corps of Engineers (USACE) CRD C48-73 "Permeability of Concrete" Pacific Testing Labs, Seattle, USA*

Two inch (51 mm) thick, 2000 psi (13.8 Mpa) Xypex-treated concrete samples were pressure tested up to a 405 ft. (124m) water head (175 psi/1.2 Mpa), the limit of the testing apparatus. While untreated samples showed marked leakage, the Xypex-treated samples (as a result of the crystallisation process) became totally sealed and exhibited no measurable leakage.

*DIN 1048 "Water Impermeability of Concrete" Bauteil – Corporation for Research & Testing of Building Materials, Augsburg, Germany*

Twenty cm thick Xypex-treated concrete samples were pressure tested up to 7 bars (230 ft./70m water head) for 24 hours to determine water impermeability. While the reference specimens measured water penetration up to a depth of 92 mm, Xypex-treated samples measured water penetration of zero to an average of 4 mm.

*ONORM B 3303 "Water Permeability of Concrete" Technologisches Gerwebemuseum, federal Higher Technical Education & Research Institute, Vienna, Austria*

Xypex-treated concrete samples were pressure tested to a maximum 7 bars (230 ft./70 m water head) for 10 days. Test revealed that while 25 ml of water had penetrated the untreated concrete samples, zero ml had penetrated the Xypex-treated samples.

Test specimens were then broken and showed water penetration to a depth of 15 mm on untreated samples but no measurable water penetration on the Xypex-treated samples.

*CSN 1209/1321 "Impermeability and Resistance to Pressurised Water" Institute of Civil Engineering, Technology and Testing, Bratislava, Slovak Republic*

Xypex-treated and untreated concrete samples were exposed to 1.2 Mpa of pressure to determine water permeability. Results showed the Xypex-treated samples provided effective protection against hydrostatic water pressure. Treated and untreated samples were also subjected to contact with silage juices and various petroleum products (e.g. diesel oil, transformer oil, gasoline) at 14kPa for 28 days. The Xypex-treated samples significantly reduced the penetration of these solutions.

## CHEMICAL RESISTANCE

### FREEZE/THAW DURABILITY

*ASTM C 672 "Standard Test Method for Scaling Resistance of Concrete Surfaces Exposed to De-icing Chemicals" Twin City Testing Lab, St. Paul, USA*

Xypex-treated samples restricted chloride ion concentration to below the level necessary to promote electrolytic corrosion of reinforcing steel. Visual examination of untreated panels after 50 freeze/thaw cycles showed a marked increase in surface deterioration compared to Xypex-treated samples.

## POTABLE WATER EXPOSURE

*NSF 61 "Drinking Water System Component-Health Effects" NSF International, Ann Arbor, Michigan*

Exposure testing of potable water in contact with Xypex-treated samples indicated no harmful effects.

### RADIATION RESISTANCE

*U.S.A. Standard No. N69 "Protective Coatings for the Nuclear Industry" Pacific Testing Labs, Seattle, USA*

After exposure to  $5.76 \times 10^4$  rads of gamma radiation, the Xypex treatment revealed no ill effects or damages.

## APPLICATION PROCEDURES

1. Surface preparation Concrete surfaces to be treated must be clean and free of laitance, dirt, film, paint, coating or other foreign matter. Surfaces must also have an open capillary system to provide "tooth and suction" for the Xypex treatment. If surface is too smooth (e.g. where steel forms are used) or covered with excess form oil or other foreign matter, the concrete should be lightly sandblasted, waterblasted, or etched with muriatic (HCL) acid.

2. Structural repair Rout out cracks, faulty construction joints and other structural defects to a depth of 37 mm and a width of 25 mm. Apply a brush coat of Xypex Concentrate as described in steps 5 & 6 and allow to dry for 10 minutes. Fill cavity by tightly compressing Dry-Pac into the groove with pneumatic packing tool or with hammer and wood block. Dry-Pac is prepared by mixing six parts Xypex Concentrate powder with one part water to a dry, lumpy consistency.

Note:

1. Against a direct flow of water (leakage) or where there is excess moisture due to seepage, use Xypex Patch'n Plug then Xypex Dry-Pac followed by a brush coat of Xypex Concentrate (refer to Xypex Specification and Application Manual for full details).

2. For expansion joints or chronic moving cracks, flexible materials such as expansion joint sealants should be used.

3. Wetting concrete Xypex requires a saturated substrate and a damp surface. Concrete surfaces must be thoroughly saturated with clean water prior to the application so as to aid the proper curing of the treatment and to ensure the growth of the crystalline formation deep within the pores of the concrete. Remove excess surface water before the application. If concrete surface dries out before application, it must be re-wetted.

4. mixing for slurry coat Mix Xypex powder with clean water to a creamy consistency in the following proportions:

For Brush Application

0.65 - 0.8 kg/m<sup>2</sup>

5 parts powder to 2 parts water

1.0 kg/m<sup>2</sup>

3 parts powder to 1 part water

For Spray Application

0.65 - 0.8 kg/m<sup>2</sup>

5 parts powder to 3 parts water

(ratio may vary with equipment type)

Do not mix more Xypex material than can be applied in 20 minutes. Do not add water once mix starts to harden. Protect hands with rubber gloves.

5. APPLYING XYPEX Apply Xypex with a semi-stiff nylon bristle brush, push broom (for large horizontal surfaces) or specialized spray equipment. The coating must be uniformly applied and should be just under 1.25 mm. When a second coat (Xypex Concentrate or Xypex Modified) is required, it should be applied after the first coat has reached an initial set but while it is still "green" (less than 48 hours). Light pre-watering between coats may be required due to drying.

The Xypex treatment must not be applied under rainy conditions or when ambient temperature is below 4°C. For recommended equipment, contact Xypex Australia or your nearest Xypex distributor.

6. **CURING** A misty fog spray of clean water must be used for curing the Xypex treatment. Curing should begin as soon as the Xypex has set to the point where it will not be damaged by a fine spray of water. Under normal conditions, it is sufficient to spray Xypex treated surfaces three times per day for two to three days. In hot or arid climates, spraying may be required more frequently. During the curing period, the coating must be protected from rainfall, frost, wind, the puddling of water and temperatures below 2°C for a period of not less than 48 hours after application. If plastic sheeting is used as protection, it must be raised off the Xypex to allow the coating to breathe. Xypex Gamma Cure may be used in lieu of water curing for certain applications (consult with Xypex Australia's Technical Department or your local Xypex representative).

Note: For concrete structures that hold liquids (e.g. reservoirs, swimming pools, tanks, etc.), Xypex should be cured for three days and allowed to set for 12 days before filling the structure with liquid.

## TECHNICAL SERVICES

For more instructions, alternative application methods, or information concerning the compatibility of the Xypex treatment with other products or technologies, contact the Technical Department Xypex Australia or your local Xypex representative safe handling information

## SAFE HANDLING INFORMATION

Xypex is alkaline. As a cementitious powder or mixture, Xypex may cause significant skin and eye irritation. Directions for treating these problems are clearly detailed on all Xypex buckets and packaging. The Manufacturer also maintains comprehensive and up-to-date Material Safety Data Sheets on all its products. Each sheet contains health and safety information for the protection of your employees and customers. Contact Xypex Australia or your local Xypex representative to obtain copies of Material Safety Data Sheets prior to product storage or use.

## WARRANTY

Concrete Waterproofing Manufacturing Pty Ltd (trading as Xypex Australia) (the "Manufacturer") warrants that the products manufactured by it shall be free from material defects and of a consistent quality. Should any of the products be proven defective, the liability of the Manufacturer shall be limited to replacement of the product ex-factory. The Manufacturer gives no warranty as to fitness of the products for any particular purpose. The user shall: determine the suitability of the product for its intended use; comply with the directions for use and safe handling information available from Xypex; where necessary, engage an experienced Xypex applicator; and assume all risks and liabilities in connection with the use of this product.

**Open MSDS for Modified**  
[MSDS\05msds.doc](#)



XYPEX is a registered trademark of Xypex Chemical Corporation

Distributed in Singapore and Riau Islands by JINGSLINK MARKETING PTE. LTD.  
- XYPEX SINGAPORE

10 Ubi Crescent #02-45 Ubi Techpark, Singapore 408564  
Telephone: (65) 6299 5836 Facsimile: (65) 6299 5893  
Email: [sales@jmpl.com.sg](mailto:sales@jmpl.com.sg) Website: [www.jmpl.com.sg](http://www.jmpl.com.sg)